

WHAT IS CLAIMED IS:

1. An electroconductive device, comprising: a pair of oppositely disposed electrodes, and a luminescence layer and an electroconductive layer
5 disposed between the electrodes, wherein

the electroconductive layer comprises a mixture of a plurality of organic compounds which are mutually structural isomers and include a major component and a minor component, the mixture
10 comprising the major and minor components in a (major component)/(minor component) ratio of 1/1 to 9/1.

2. A device according to Claim 1, wherein the organic compounds are represented by the following
15 formula (1):













wherein Ar denotes a connected ring structure comprising two single rings connected with each other via a single bond or two fused rings connected with
20 each other via a single bond; X and X' independently denote a single bond, -O-, -S-, -OOC- or -COO-; R and R' independently denote -H, -F or a linear or branched alkyl group having 1 - 20 carbon atoms capable of including one methylene group which can be replaced
25 with -O-, -S-, -CH=CH- or -C≡C-; and m and n are an integer of 1 - 8, with the proviso that R and R' cannot be -H at the same time when X and X' are a

single bond.



3. A device according to Claim 1, wherein Ar in the formula (1) is a connected ring structure comprising two fused rings connected with each other via a single bond, each of said two fused rings comprising 2 - 5 rings.

4. A device according to Claim 2, wherein Ar in the formula (1) is a connected ring structure represented by any one of the following formulas (a) to (n):







5



10



15

wherein CH is optionally substituted with N or NH, and CH₂ is optionally substituted with S or O.

20

5. A device according to Claim 2, wherein Ar in the formula (1) is a connected ring structure represented by the following formula (2):



25

wherein A and B independently denote any one of phenyl-diyl, pyridine-diyl, pyrazine-diyl, pyrimidine-diyl, pyridazine-diyl, indene-diyl, indolizine-diyl, isoindole-diyl, indole-diyl, purine-diyl, naphthalene-diyl, quinoline-diyl, isoquinoline-diyl, quinoxaline-diyl, 1,5-naphthyridine-diyl, 1,6-naphthyridine-diyl,

1,7-naphtharidine-diyl, 1,8-naphthyridine-diyl,
quinazoline-diyl, cinnoline-diyl, pyrido[2,3-
b]pyrazine-diyl, pyrazino[2,3-b]pyrazine-diyl,
pteridine-diyl, biphenylene-diyl, fluorene-diyl,
5 carbazole-diyl, thianthrene-diyl, phenalene-diyl,
phenanthridine-diyl, phenanthrene-diyl, anthracene-
diyl, chrysene-diyl, acridine-diyl, perimidine-diyl,
phenanthroline-diyl, phenazine-diyl, phenothiazine-
diyl, phenoxathin-diyl, indan-diyl, coumaran-diyl,
10 phthalan-diyl, chroman-diyl, isochroman-diyl,
thiachroman-diyl, isothiachroman-diyl, and
thiaxanthene-diyl.

6. A device according to Claim 5, wherein A in
15 the formula (2) is quinoxaline-diyl.

7. A device according to Claim 5, wherein $R=R'$,
 $X=X'$ and $m=n=1$ are satisfied in the formula (1), and
 $A=B$ is satisfied in the formula (2) to form a
20 symmetric structure having a center of symmetry.

8. A device according to Claim 1, wherein the
mixture of a plurality of organic compounds is in an
amorphous state.

25

9. An electroluminescence device, comprising: a
pair of oppositely disposed electrodes, and a

luminescence layer and a carrier injection layer
and/or a carrier transport layer disposed between the
electrodes, wherein

the carrier injection layer and/or the
5 carrier transport layer comprises the
electroconductive layer of the electroconductive
device according to Claim 1.

10. A device according to Claim 9, wherein the
10 device comprises the luminescence layer and the
carrier injection layer disposed between the
electrodes, the carrier injection layer being an
electron injection layer.

15 11. A process for producing an electroconductive
device of the type comprising a pair of oppositely
disposed electrodes and an electroconductive layer
disposed between the electrodes, said process
comprising:

20 a step of forming an electroconductive layer
comprising a mixture of a plurality of organic
compounds between the electrodes, the organic
compounds being mutually structural isomers and
including a major component and a minor component;
25 wherein

the mixture comprises the major and minor
components in a (major component)/(minor component)

096441 092701

ratio of 1/1 to 9/1.

12. A process according to Claim 11, wherein the
electroconductive layer is formed through vacuum
5 deposition.

10

15

20

25

09341 09270
T0220 T4E6E60